

Product Data

Limestone and Masonry Afterwash PAGE 1 OF 2

Description and use

Limestone and Masonry Afterwash, a mild organic acid cleaning compound, neutralises and brightens surfaces that have been prewashed with an alkaline cleaner. Limestone Afterwash will not damage most masonry surfaces.

Advantages

- Does not contain hydrochloric or hydrofluoric acid
- Concentrated for economy
- Easy to apply with brush, roller or sprayer
-

Always test.

Substrate	Type		m ² per litre
Architectural Concrete Block	Smooth	Yes	2 – 3
	Split Faced	Yes	
	Burnished	Yes	
	Ribbed	Yes	
Marble Travertine Limestone	Polished	No	N/A
	Unpolished	Yes	3 – 5
Granite	Polished	No	N/A
	Unpolished	Yes	4 – 6
Sandstone	Unpolished	Yes	3 – 4
Slate	Unpolished	Yes	3 – 5
Fired Clay	Brick	Yes	3 – 4
	Tile	Yes	
	Terracotta	Yes	
	Pavers	Yes	
Concrete	Block	Yes	3 - 4
	Brick	Yes	
	Tile	Yes	
	Precast Panels	Yes	
	Pavers	Yes	
	Cast in place	Yes	

Technical Data

Form:	Clear Liquid
Specific Gravity:	1.023
Flashpoint:	>95°C
pH:	1.6
Freeze Point:	-7°C

Preparation

Protect surrounding surfaces and beware of wind drift.

Cleaning effectiveness is reduced when surface and air temperatures fall below 10°C. Do not apply when temperatures are below -1°C. If freezing conditions exist prior to application, allow adequate time for masonry to thaw.

Equipment

Apply using a soft fibred masonry brush or low pressure compression sprayer. Rinse using a pressure washer.

Pretesting

Always test each type of surface and stain before overall application to ensure suitability, dilution rates and desired results. Apply test area according to the following application procedures. Allow area to dry thoroughly before inspection and approval.

Dilutions

Dilute one part fresh water to one part concentrated cleaner before application. Pour water into empty bucket, then carefully add Limestone Afterwash. Never pour water into the cleaner.

Application Instructions

1. Pre-wet the surface.
2. Allow the Afterwash to remain on the surface for 3 to 5 minutes.
3. Pressure rinse from the bottom of the treated area to the top. Make sure to cover each portion of the masonry surface with the concentrated stream of water. To avoid streaking, keep wall surfaces immediately below area being cleaned running wet and free of cleaner rundown and residues.

Coverage Rates

Coverage rates will vary according to surface porosity, texture and severity of staining.

Packing

5 litre plastic container.

Safety Information

Causes burns. Wear suitable PPE - goggles, face shield, protective clothing and gloves to avoid splash to bear skin or eyes. Always refer to material safety data sheet before use.

Technical Data

Contains acetic acid.

Shelf Life

Limestone and Masonry Afterwash may be stored for up to 3 years in a tightly sealed, unopened container.

The information contained on here & on other Data Sheets / MSDS Sheets is based on the present state of knowledge and current national legislation. It provides guidance on health, safety and environmental aspects of the products and should not be construed as any guarantee of technical performance or suitability for particular applications. The responsibility to ensure safe working conditions within the workplace remains with the user. The health hazard and general information contained within Material Safety Data Sheet are given as a guide to the precautions required to maintain a safe work environment.

Malcolm Smith – Power Cleaning

45 Roundponds, Melksham, Wiltshire. SN12 8DW

Tel: 01225 707200 / Mobile: 07850 119990

Ssles@malcleanse.co.uk

www.powerwashinguk.co.uk

www.malcleanse.co.uk